

## J-7000 *Rulon Comparable: 641*



### TECHNICAL DATA

PROPERTY	ASTM METHOD	VALUE
Specific Gravity	D792	2.27
Tensile Strength	D4894	2,890 psi
Elongation @ Break	D4894	270%
Compressive Modulus	D695	72,000 psi
Compressive Strength @ 0.2% Offset	D695	1,250 psi
Compressive Strength @ 5% Strain	D695	1,970 psi
Hardness	D2240	60-66 Shore D
Temperature Range	—	-300 to 500 F