

## J-8000 *Rulon Comparable: 123*



### TECHNICAL DATA

PROPERTY	ASTM METHOD	VALUE
Specific Gravity	D792	2.14
Tensile Strength	D4894	2,640 psi
Elongation @ Break	D4894	190%
Compressive Modulus	D695	56,000 psi
Compressive Strength @ 0.2% Offset	D695	1,190 psi
Compressive Strength @ 5% Strain	D695	1,880 psi
Hardness	D2240	58-63 Shore D